


SHISHA

Flat Shisha Charcoal

Low-profile coconut tablets at 25 x 25 mm, in 17 or 20 mm thickness, at 80% fixed carbon and 70 to 80 minutes per load.

Coconut shell

Flat



- 25 mm footprint, 17 or 20 mm high: sits low on foil
- F17 (70 min) and F20 (80 min)
- Lights in about 7 minutes, no spark
- Custom branding on boxes and cartons

SPECIFICATIONS

Fixed carbon	80% min	Ignition time	7 minutes
Ash content	1.9% max, white	Burning temperature	650°C
Moisture	5% max	Burn time	70 to 80 min
Volatile matter	14% max	Size	25 x 25 mm, 17 or 20 mm thick
Calorific value	7,500 kcal/kg min	Packaging	500 g, 1 kg, 3 kg inner boxes

SIZES AND PRODUCT CODES

CODE	SIZE	BURN TIME	PACKAGING
F17 17 mm flat	17 x 25 x 25 mm	70 minutes	500 g, 1 kg, 3 kg inner box
F20 20 mm flat	20 x 25 x 25 mm	80 minutes	500 g, 1 kg, 3 kg inner box

TRADE TERMS

HS CODE	INCOTERMS	CERTIFICATIONS		
4402.90.10	FOB · CIF · EXW	ISO 9001:2015	MSDS	Self-heating test (IMO) Factory audit on request

OVERVIEW

Flat shisha charcoal suits shallow bowls, small heat management devices, and price-sensitive retail packs. It has the same 25 mm footprint as a cube at two thirds of the height, so it sits low on the foil and lights faster. Pressed from coconut shell to the same 80% fixed carbon and 1.9% white ash spec as our cubes, in two thicknesses: F17 at 17 mm (70 minutes) and F20 at 20 mm (80 minutes).

The values shown are contract specs. Per-lot figures are confirmed on the batch CoA when the container is loaded.

PT FoodHub Collective Indonesia

Jl. Tb Simatupang Kav. 1, Pasar Minggu
Jakarta Selatan 12560, Indonesia

sales@indonesiacharcoal.com

+6289675583985
indonesiacharcoal.com

Scan for the live
product page

