BBQ

Hexagonal BBQ Charcoal Briquettes

Hexagonal coconut grilling briquettes at 60 mm, in 10 or 15 mm thickness, at 80% fixed carbon and 2.5 to 3.5 hours per load.

Coconut shell | Hexagonal

- Up to 3.5 hours per bed, even heat
- B10 (2.5 h) and B15 (3.5 h)
- 60 mm hex tiles into a gap-free bed
- Custom branding on retail bags

SPECIFICATIONS

Fixed carbon	80% min	Ignition time	7 minutes
Ash content	1.9% max, white	Burning temperature	650°C
Moisture	5% max	Burn time	2.5 to 3.5 hours
Volatile matter	14% max	Size	60 mm hex, 10 or 15 mm thick
Calorific value	7,500 kcal/kg min	Packaging	5 kg to 20 kg bags

SIZES AND PRODUCT CODES

CODE	SIZE	BURN TIME	PACKAGING
B10 60 x 10 mm hex	60 mm (D) x 10 mm (L)	2.5 hours	5 kg, 10 kg, 20 kg bag
B15 60 x 15 mm hex	60 mm (D) x 15 mm (L)	3.5 hours	5 kg, 10 kg, 20 kg bag

TRADE TERMS

HS CODE
4402.90.10

INCOTERMS
FOB · CIF · EXW

CERTIFICATIONS
ISO 9001:2015 | MSDS | Self-heating test (IMO) | Factory audit on request

OVERVIEW

Wide hexagonal grilling briquettes pressed from coconut shell for restaurants, yakiniku and shawarma grills, and premium retail. The 60 mm hex tiles into a flat, gap-free bed, so the heat across the grate is even and one bed lasts a whole service: 2.5 hours for the 10 mm B10 and 3.5 hours for the 15 mm B15. The spec is the same 80% fixed carbon and 1.9% white ash as the rest of the range, with no coal dust, borax, or accelerant.

The values shown are contract specs. Per-lot figures are confirmed on the batch CoA when the container is loaded.

PT FoodHub Collective Indonesia

Jl. Hajjah Tutty Alawiyah No.7, RT.2/RW.5, Kalibata, Kec. Pancoran
Kota Jakarta Selatan, Daerah Khusus Ibukota Jakarta 12740

sales@indonesiacharcoal.com

+6289675583985
indonesiacharcoal.com

Scan for the live product page