

BBQ

Hexagonal BBQ Charcoal Briquettes

Hexagonal coconut grilling briquettes at 60 mm, in 10 or 15 mm thickness, at 80% fixed carbon and 2.5 to 3.5 hours per load.

Coconut shell

Hexagonal



- Up to 3.5 hours per bed, even heat
- 60 mm hex tiles into a gap-free bed
- B10 (2.5 h) and B15 (3.5 h)
- Custom branding on retail bags

SPECIFICATIONS

Fixed carbon	80% min	Ignition time	7 minutes
Ash content	1.9% max, white	Burning temperature	650°C
Moisture	5% max	Burn time	2.5 to 3.5 hours
Volatile matter	14% max	Size	60 mm hex, 10 or 15 mm thick
Calorific value	7,500 kcal/kg min	Packaging	5 kg to 20 kg bags

SIZES AND PRODUCT CODES

CODE	SIZE	BURN TIME	PACKAGING
B10 60 x 10 mm hex	60 mm (D) x 10 mm (L)	2.5 hours	5 kg, 10 kg, 20 kg bag
B15 60 x 15 mm hex	60 mm (D) x 15 mm (L)	3.5 hours	5 kg, 10 kg, 20 kg bag

TRADE TERMS

HS CODE	INCOTERMS	CERTIFICATIONS		
4402.90.10	FOB · CIF · EXW	ISO 9001:2015	MSDS	Self-heating test (IMO) Factory audit on request

OVERVIEW

Wide hexagonal grilling briquettes pressed from coconut shell for restaurants, yakiniku and shawarma grills, and premium retail. The 60 mm hex tiles into a flat, gap-free bed, so the heat across the grate is even and one bed lasts a whole service: 2.5 hours for the 10 mm B10 and 3.5 hours for the 15 mm B15. The spec is the same 80% fixed carbon and 1.9% white ash as the rest of the range, with no coal dust, borax, or accelerant.

The values shown are contract specs. Per-lot figures are confirmed on the batch CoA when the container is loaded.

PT FoodHub Collective Indonesia

Jl. Tb Simatupang Kav. 1, Pasar Minggu
Jakarta Selatan 12560, Indonesia

sales@indonesiacharcoal.com

+6289675583985
indonesiacharcoal.com

Scan for the live
product page

